

Anwendung / Utilisation / Use / Utilizzazione

Quick Multicolor Gestaltung in der Mikrowelle

1. Feuchte Seide in Mikrowellen geeignete Schale geben und nach belieben knittern oder falten. 2. Mit Quick Color Farben einfärben. 3. 3-4 Min. bei ca. 450 Watt in die Mikrowelle geben. 4. Kalt auswaschen und feucht bügeln.

Quick création multicolore au microonde


1. Froissez ou plissez votre soie humide dans un plat allant au microonde 2. Colorez la à l'aide des Quick Colors. 3. Enfournez pour 3-4 minutes à 450 watts. 4. Rincez à l'eau froide et repassez encore humide.

Quick rainbow colour for microwave

1. Put damp silk in a microwavable dish. Crinkle or fold the silk. 2. Add Quick Colors as desired. 3. Microwave for 3-4 Min. at approx 450 Watts. 4. Rinse in cold water until water runs clear and iron dry.

Quick creazione multicolore nel forno a microonde

1. Piegare o raggrinzare la seta umida e mettere su un piatto resistente al forno a microonde. 2. Tingere con Quick Color. 3. Lasciare nel forno a microonde per 3-4 minuti a ca. 450 watt. 4. Risciacquare con acqua fredda e stirare ancora umida.




- Zwei Spiralen im feuchten Tuch formen.
- Formez deux spirales dans le foulard humide.
- Twist the damp scarf into two spirals.
- Formare due spirali nel scialle umido.



- Knoten in das feuchte Tuch machen.
- Faites des noeuds dans le foulard humide.
- Tie some knots in the damp scarf.
- Fare dei nodi del scialle umido.



Falttechniken / Techniques plissés / Tie-dye techniques / Tecniche di piegare



- Feuchtes Tuch 3 mal falten.
- Pliez 3 fois le foulard humide.
- Fold the damp scarf 3 times.
- Piegare il scialle 3 volte.



Quick Color

- Feuchtes Tuch an verschiedenen Stellen zu Spitzen zwirbeln.
- Faites des tortillons dans le foulard humide.
- Twist some points in the damp scarf.
- Fare dei attorcigliamenti nel scialle umido.



Unifärbung Teinture Uni Dip dyeing Tintura unita

Quick Color Unifärbung

Für ein Seidenruch, 2l Wasser, 100ml weissen Essig und Quick Color (0,5-20ml je nach Farbintrastät) im Topf auf ca. 60°C erhitzen. Feuchte Seide zugeben und färben bis das Wasser wieder klar wird. Kalt auswaschen und feucht bügeln.

Quick Color Teinture Uni


Pour un foulard en soie, chauffez dans un récipient, 2l d'eau, 100ml de vinaigre blanc et la Quick Color (0,5-20ml selon l'intensité). A 60°C, ajoutez la soie humide et continuez de chauffer jusqu'à ce que l'eau redevenue transparente. Rincez à l'eau froide et repassez encore humide.

Quick Color dip dyeing


For 1 silk scarf, Put 2ltr water, 100ml spirit vinegar and Quick Color (0,5-20ml depending on depth of colour required) in a pan and heat to about 60°C. Add damp scarf and dye until the water becomes clear. Rinse thoroughly in cold water and iron dry.

Quick Color Tintura unita


Per un scialle, 2l d'acqua, 100ml d'aceto bianco e Quick Color (0,5-20ml dipende dall'intensità del colore) mettere in una pentola a 60°C. Aggiungere la seta umida e lasciare tingere finché l'acqua ritornerà chiara. Lavare con l'acqua fredda e stirare ancora umida.



- Feuchtes Tuch wie eine Ziehharmonika falten.
- Plissez le foulard humide en accordéon.
- Fold the damp scarf like an accordion.
- Piegare il scialle umido come una fisarmonica.



- Feuchtes Tuch zu einem Strudel formen.
- Faites une spirale dans le foulard humide.
- Form the damp scarf into a spiral.
- Formare una spirale nel scialle umido.



- Feuchtes Tuch knittern.
- Froissez le foulard humide.
- Scrumple damp scarf.
- Raggrinzare il scialle umido.



- Feuchtes Tuch rollen und in regelmäßigen Abständen Knoten machen.
- Roulez le foulard humide et faites des noeuds réguliers.
- Roll the damp scarf and tie knots in regular spaces.
- Rotolare il scialle umido e fare dei nodi regolari.



- Feuchtes Tuch in 2 Richtungen drehen.
- Torsadez le foulard humide en 2 direction opposées.
- Turn the damp scarf in 2 directions.
- Girare il scialle umido in 2 direzioni opposte.





QUICK COLOR **MICROWAVE DYES**

**SO QUICK AND EASY YOU WONT BELIEVE
IT!**

- 1. DAMP YOUR SILK**
- 2. SCRUNCH OR FOLD THE SILK**
- 3. PLACE IN A MICROWAVABLE DISH**
- 4. ADD QUICK COLOURS AS DESIRED**
- 5. MICROWAVE 4-5 MINUTES AT APPROX,
450WATTS***
- 6. RINSE IN COLD WATER UNTIL WATER RUNS
CLEAR AND IRON DRY**

ARTY'S TIPS: Choose your Quick Colours carefully, opting for colours that you know will harmonise well. Remember that if you choose two colours, they will create a third colour on your silk!

Spiral your silk! Lay wet silk out flat, take the handle of a wooden spoon and place upright in centre of silk. Twist handle, spiralling silk as you go. Encourage silk to lay in folds around the spiralled centre. When all silk is twisted, carefully remove spoon handle. Apply Quick Color, being especially careful to put plenty of dye around the spiralled centre of the

silk where it is at its thickest. Place carefully in microwavable dish and following instructions for fixing as above.

Fold your silk! Lay wet silk out and pleat as in a concertina. Apply Quick Color as desired and fix. For tartan effect, wet silk again and pleat in opposite direction. Fix as above. Gorgeous if you use yellow, pink and turquoise!

Knot your silk! Tie knots in wet silk or wind elastic bands around bunches of silk. Apply dye as before, concentrating particularly on areas where silk has been knotted.

Salt your silk! Once silk has been treated with Quick Color, sprinkle ARTY'S Effect Salt Crystals randomly, leave for ten minutes or so, scrunch lightly and microwave as above. Brush off any remaining dry salt crystals, rinse and iron as above.

Wax your silk! Using ARTY'S Cold Wax, apply either with brush or through a pipette, to damp silk. Try either drying wax off or working whilst it is still damp. Add Quick Color as desired, microwave as above. Cold Wax will wash away under hot water along with loose dye.

Quick Color Microwave dyes are highly concentrated so try diluting to achieve soft pastel tones. Dilute some colours and use others at full strength for texture and interest.

**If you are using a thicker silk or dyeing a tie, it may be that extra time is needed. However, to prevent scorching, additional time should be added only 30 seconds at a time.*